



# Technical Bulletin

2400 Boston Street, Suite 200, Baltimore, Maryland 21224  
Phone: 410-675-2100 or 800-543-3840

Revised: 5/3/05

## DAP® Bondex® Quick Plug® Hydraulic Cement

- For plugging and sealing holes in concrete and masonry
- Creates a watertight seal, even while water is flowing
- Can also be used as an anchoring cement

**Packaging:** 2.5 lb. box, 5 lb. box, 10 lb. pail  
**Color:** Gray  
**UPC Number:** 14084 (2.5 lb.), 14086 (5 lb.), 14090 (10 lb.)

### Company Identification:

**Manufacturer:** DAP Inc.  
**Marketed by:** DAP Inc., 2400 Boston Street, Suite 200, Baltimore, Maryland 21224  
**Usage Information:** DAP HELPLINE: 888-DAP-TIPS, 9:00 am to 7:00 pm EST.  
**Order Information:** 800-327-3339  
**Fax Number:** 410-534-2650  
Also, visit the DAP website at [www.dap.com](http://www.dap.com).

### Product Description:

DAP® Bondex® Quick Plug® Hydraulic Cement may be used to stop running water through deep cracks and holes in concrete and masonry surfaces. DAP® Bondex® Quick Plug® Hydraulic Cement may be used for interior and exterior applications and when mixed properly, it creates a watertight seal in 3 to 5 minutes, even while water is flowing. DAP® Bondex® Quick Plug® Hydraulic Cement can also be used to anchor machinery and other equipment in concrete.

### Suggested Uses

- *For stopping water flow and permanently sealing deep cracks and holes in all grades of concrete.*
- *Also ideal for use as an anchoring cement.*

### Surface Preparation & Application

- Chisel holes to enlarge them by at least 1/4" and scrape clean. Remove any loose or chipped concrete. Make sure that the surface to be patched is damp.
- Add DAP® Bondex® Quick Plug® Hydraulic Cement to clear water in clean container mixing 3 parts powder to 1 part water by volume. Stir the mixture until it reaches a putty-like paste. The mixture will begin to set in 3 to 5 minutes so only mix as much material as you can use in this time. Discard any material that has begun to set.
- Hold compound in your gloved hand until it becomes warm. Force it firmly into the hole and continue pressing it in place for 5 minutes. Within 3 to 5 minutes after setting, trim or brush away any excess cement for a smooth finish.

**FOR BEST RESULTS**

- Always apply to a damp surface.
- Apply from the top of the opening down.
- Keep the patched area damp for several hours after the application.
- If painting is desired, always use a good quality latex-based or masonry paint for a professional finish.

**Physical & Chemical Characteristics:**

Working Time: 3 to 5 Minutes  
 Setting Time: 5 Minutes  
 Final Cure: 28 Days  
 Packaging:

<u>UPC</u>	<u>Size</u>	<u>Container</u>
14084	2 1/2 lb.	Box
14086	5 lb.	Box
14090	10 lb.	Pail
10050	454g	Box
10060	1.13kg	Box
10070	5kg	Pail
10080	10kg	Pail

MSDS No.: 00079705001

**Clean Up:**

Wash skin and hands with soap and water. Cured material must be scraped away

**Safety:**

See product label and Material Safety Data Sheet (MSDS) for safety information. You can request an MSDS by visiting our website at [www.dap.com](http://www.dap.com) or by calling 888-DAP-TIPS.

**Warranty Information:**

If you are not satisfied with this product’s performance when used as directed, return used container and sales receipt to DAP Inc., Technical Customer Service, 2400 Boston Street, Suite 200, Baltimore, MD 21224 for product replacement or sales price refund. DAP will not be liable for incidental or consequential damages.